








Ultraviolet screener blends.

Patent number: EP0424153
Publication date: 1991-04-24
Inventor: MCCLURE GEORGE RICHARD (US)
Applicant: DU PONT (US)
Classification:
- **international:** *C08J5/18; C08K5/00; C08J5/18; C08K5/00;* (IPC1-7):
C08J5/18; C08K5/00; C08L27/12
- **european:** C08J5/18; C08K5/00P6
Application number: EP19900311448 19901018
Priority number(s): US19890423364 19891019

Also published as:

 US5254608 (A1)
 JP3192143 (A)
 EP0424153 (A3)
 EP0424153 (B1)

Cited documents:


 US3018269
 DE3429224
 JP2034588

Report a data error here

Abstract of EP0424153

A blend of ultraviolet screeners which results in excellent screening, but which does not interfere with the optical clarity of polymeric films such as poly(vinyl fluoride).

Data supplied from the **esp@cenet** database - Worldwide



(19)

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 0 424 153 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:
03.01.1996 Bulletin 1996/01

(51) Int Cl.⁶: **C08J 5/18, C08K 5/00,
C08L 27/12**

(21) Application number: **90311448.6**

(22) Date of filing: **18.10.1990**

(54) **Ultraviolet screener blends**

Ultraviolett-Abschirmmischungen

Mélanges de screener ultraviolet

(84) Designated Contracting States:
DE FR GB IT

(30) Priority: **19.10.1989 US 423364**

(43) Date of publication of application:
24.04.1991 Bulletin 1991/17

(73) Proprietor:
**E.I. DU PONT DE NEMOURS AND COMPANY
Wilmington, Delaware 19898 (US)**

(72) Inventor: **McClure, George Richard
Claymont, Delaware 19703 (US)**

(74) Representative: **Jones, Alan John et al
London, WC1A 2RA (GB)**

(56) References cited:
DE-A- 3 429 224 US-A- 3 018 269

• **PATENT ABSTRACTS OF JAPAN vol. 14, no.
188 (C-710)(4131) 17 April 1990 & JP-A-2 034
588 (DAINIPPON INK & CHEM INC) 5 February
1990**

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

DescriptionBackground of the Invention

5 Fluoropolymer films have long been used in applications where the finished film is exposed to ultraviolet light. For example, poly(vinyl fluoride) films are often used as a protective surface on building materials such as aluminum and poly(vinyl chloride) house siding. To prevent degradation, by the ultraviolet light, of film itself and either a bonding layer or a substrate beneath the film, screeners have often been incorporated into the films.

10 In the past, poly(vinyl fluoride) films were typically used which had been molecularly oriented in one or both of the machine and transverse directions. More recently, however, unoriented films have been needed for protective applications in which a high degree of clarity was also desired. It was found that the ultraviolet light screeners, of the types and in the concentrations previously used in poly(vinyl fluoride) films, did not provide the optical clarity required for certain decorative applications.

15 Summary of the Invention

The present invention provides fluoropolymer films having ultraviolet screeners which result in excellent screening, but which do not interfere with the optical clarity of films.

20 Specifically, the instant invention provides, in a fluoropolymer film comprising up to about 10 weight % of ultraviolet light absorber, the improvement wherein the film comprises at least two ultraviolet light absorbers, each absorber having a molecular weight of less than 5000 and less than that which will form a visible separate phase in the fluoropolymer; each absorber present in a quantity of up to 2.5 parts by weight per hundred parts by weight of resin, but below the saturation level of that absorber in the fluoropolymer; and each absorber having a molecular structure which differs chemically from each other absorber.

25 Detailed Description of the Invention

The present invention is applicable to fluoropolymer films, such as those prepared from tetrafluoroethylene polymers and copolymers. The present invention is particularly well suited to poly(vinyl fluoride) films, the nature and preparation of which are described in detail in U.S. Patents 3,139,470, 2,953,818, 2,419,008, 2,510,783 and 2,599,300. Specifically, the invention is applicable to those films containing up to 10 weight % of ultraviolet light absorber, and especially from 1 to 7.5 weight %.

35 The ultraviolet light absorbers which can be used in the present invention are selected from the general classes of monomeric or low molecular weight oligomeric absorbers previously used in the art. These include hydroxy benzophenones, hydroxy benzo triazoles, oxanilides and substituted cyanoacrylates. Specific compounds of these types which can be used are more fully described in U.S. Patents 4,314,933, 3,278,589 and 3,935,164. Still other known stabilizers which can be used in the present invention are hindered amine stabilizers, which can also neutralize the species that ultraviolet light generates.

40 In accordance with the instant invention, at least two ultraviolet light absorbers are incorporated into the fluoropolymer film. Each ultraviolet light absorber has a molecular weight less than that which will form a visible separate phase in the polymer. Accordingly, the absorbers are substantially monomeric, or of such lower oligomeric molecular weight that they will neither form a visible separate phase or agglomerate to form such a phase at the concentration used. While the specific molecular weight will vary, molecular weights of the absorbers should not exceed 5,000.

45 Each ultraviolet light absorber is incorporated into the polymer blend in a quantity below the saturation level of that absorber in the polymer, that is, the percentage at which the absorber is incompatible with the fluoropolymer in which it is used. Up to 2.5 parts by weight of each absorber per hundred parts of resin (phr) can be used. To provide the most complete screen of ultraviolet light in the finished product, at least three screeners are preferably used, and six or more can be beneficially used. In general, with poly(vinyl fluoride), a total absorber concentration of about 7.5 phr is adequate to render the film substantially opaque to ultraviolet light. Little additional benefit is realized with higher concentrations of absorber.

50 Each absorber must have a molecular structure which differs chemically from each other absorber. The difference can be as little as one substituent in the structure, or the absorbers can be selected from different classes of absorbers.

For poly(vinyl fluoride) films, a particularly desirable combination of ultraviolet light absorbers is that which comprises from 0.5 to 3.5 parts of at least one benzotriazole, from 0.5 to 2.0 parts of at least one benzophenone, and from 0.5 to 2.0 parts of at least one oxanilide.

55 While the mechanism of the present invention is not fully understood, it is believed to be based on Dalton's law of solubility, according to which each gas or solute in a blend will exhibit its own solubility independent of other dissolved gasses or solutes. Thus, the presence of two or more ultraviolet light absorbers, each below its solubility limit in the

polymeric material, provides an additive effect on the absorption of ultraviolet light without interfering with the optical clarity of the film through incompatibility.

The absorbers incorporated in the present films, for optimal performance, should also exhibit a low volatility. Specifically, the temperature at which 10% of the absorber is volatilized, T_{10} , is preferably greater than about 200°C.

The absorbers can be incorporated into the polyvinyl films by any convenient method, depending on both the particular absorber and the film. However, it has been found to be convenient and efficient to first dissolve or disperse the absorber in the liquid that is used as the coalescing solvent for the fluoropolymer dispersion, and then milling the resulting solution into the dispersion.

The fluoropolymer films of the present invention can, as will be recognized by those skilled in the art, further comprise additives, such as plasticizers, pigments, thermal stabilizers, and flow control agents, all as previously used in such films.

The present invention will be more fully understood by reference to the following Examples, in which parts and percentages are by weight unless otherwise indicated. In these Examples, the UV screeners and hindered amines used are identified by their common names, as follows:

<u>Common Name</u>	<u>Chemical Name</u>
5 Benzotriazole-1	5-t-butyl-3-(5-chloro-2H-benzotriazol-2-yl)-4-hydroxy-benzenepropionic acid octyl ester - or "Tinuvin" 109 by Ciba Geigy.
10 Benzotriazole-2	a mixture of poly(oxy-1,2 ethane-diyl), a-(3-(3-(2H-benzotriazol-2-yl)5-(1,1-dimethylethyl)-4-hydroxyphenyl)-1-oxopropyl-w-hydroxy and Poly(oxy-1,2-ethanediyl), a-(3-(3-(2H-benzotriazole-2-yl)-5-(1,1-dimethylethyl)-4-hydroxy-phenyl-1-oxopropyl-w-3-3-(2H-benzotriazol-2-yl)-5-(1,1-dimethylethyl)-4-hydroxyphenyl)-1-oxopropoxy) or "Tinuvin" 1130 by Ciba Geigy.
25 Benzotriazole-3	2-(2-hydroxy-3,5-di(1,1-dimethylbenzyl)phenyl)-2H-benzotriazole or "Tinuvin" 900 by Ciba Geigy.
30 Benzotriazole-4	2-(3',5'-di-t-amyl-2'-hydroxyphenyl)benzotriazole or "Tinuvin" 328 by Ciba Geigy.
Benzophenone-1	2-Hydroxy-4-n-Dodecyloxybenzophenone or "UV-Check" AM 320 by Ferro Chemicals.
35 Benzophenone-2	2-Hydroxy-4-n-octyloxybenzophenone or "Cyasorb" 531 from American Cyanamid.
40 Oxanilide-1	Ethane diamide-N-(2-ethoxyphenyl)-N-(4-isodecyl phenyl) is "Sanduvor" 3206 by Sandoz Chemicals.
45 Hindered Amine-1	2,2,4,4-Tetramethyl-20-(8-lauryloxy-carbonyl)-ethyl-7-oxa-3, 20 diazaspiro (5,1,11,2) heneicosane-21-one or "Sanduvor" 3050 by Sandoz Chemicals.
50 Hindered Amine-2	8-Acetyl-3-dodecyl-7,7,9,9-tetramethyl-1,3,8-Triazaspiro (4.5) decane-2,4-dione or "Tinuvin" 440 by Ciba Geigy.
55	

Example 1

A poly(vinyl fluoride) film was prepared containing a mixture of six ultraviolet light absorbers. To 300 parts of a 33% by weight dispersion of poly(vinyl fluoride) in propylene carbonate (Tedlar 44-1000 from Du Pont) solutions of the following six absorbers were added with stirring, in the order specified:

1. 5 parts of a 20% solution of benzotriazole-1 in N-methylpyrrolidone;
2. 5 parts of a 20% solution of oxanilide-1 in propylene carbonate;
3. 5 parts of a 20% solution of benzophenone-1 in N-methylpyrrolidone;
4. 3.75 parts 20% solution of benzotriazole-2 in propylene carbonate;
5. 2.5 parts of a 20% solution of benzotriazole-3 in N-methylpyrrolidone; and
6. 2.5 parts of a 20% solution of benzophenone-2 in propylene carbonate.

This mixture was stirred 30 min. after the last addition was complete and shaken on a paint shaker for 30 minutes. Each absorber had a molecular weight less than that which will form a visible separate phase in the poly(vinyl fluoride), and each absorber was added in a quantity below the saturation level of that absorber.

The resulting mixture was coated on a 2 mil polyester film using a doctor knife and baked in a rapid recovery oven for 3 minutes at 400°F (204°C). The resulting film easily stripped from the polyester, was 1 mil in thickness, haze-free with no surface exudate and had an absorbance of 4.2 at 300 nanometers and less than 0.2 at 400 nanometers.

Example 2

To 100 parts propylene carbonate were added 0.8 parts of benzotriazole-4, 0.8 parts benzophenone-2 and 0.8 parts of oxanilide-1. The mixture was stirred and warmed until solution was complete, then 50 parts of finely divided poly(vinyl fluoride) (PV-116 from Du Pont) was added and the mixture sand milled for 30 minutes. The resulting dispersion was coated onto a glass plate using a doctor knife and baked 10 minutes at 400°F (204°C). On stripping, the resulting 27 micron film was haze-free, clear and colorless, confirming that each of the three absorbers had a molecular weight less than that which will form a visible separate phase in the poly(vinyl fluoride), and each absorber was added in a quantity below the saturation level of that absorber. The film had an absorbance of 3.1 at 300 nanometers and 0.2 at 400 nanometers.

Example 3

To 1000 parts of 33.3% poly(vinyl fluoride) dispersion in propylene carbonate (Tedlar® 44-1000, Du Pont) the following five solutions of ultraviolet light absorbers were added with stirring:

- (1) 53.4 parts of 10% solution of benzotriazole-1 in N-methylpyrrolidone;
- (2) 53.4 parts 10% solution of benzophenone-2 in propylene carbonate;
- (3) 16.7 parts 10% solution of benzotriazole-2 in propylene carbonate;
- (4) 16.7 parts 10% solution of oxanilide-1 in propylene carbonate; and
- (5) 8.3 parts of 10% solution of benzotriazole-3 in N-methylpyrrolidone.

The mixture was stirred 30 minutes after the last addition and sand milled for 30 minutes. The resulting dispersion was applied to a 3 mil polyester carrier film with a #66 Meyer rod, and baked in a high velocity oven (air velocity 10,000 ft/min) at 410°F (210°C) for 1 min. The product was a 1.3 mil, haze-free, colorless film of poly(vinyl fluoride), confirming that each of the absorbers had a molecular weight less than that which will form a visible separate phase in the poly(vinyl fluoride), and that each absorber was added in a quantity below the saturation level of that absorber. The film was easily removable from the carrier film. Absorbance of the poly(vinyl fluoride film) was 4.5 at 300 nanometers and 0.21 at 400 nanometers. By comparison a poly(vinyl fluoride) film without UV absorbers has absorbance of .09 @ 300 nm

and .01 at 400 nm.

Example 4

A film was prepared using the general procedure of Example 3, from a mixture composed of 1000 parts of 33.3% by weight dispersion of poly(vinyl fluoride) in propylene carbonate, to which were added, with stirring, the following solutions of ultraviolet light absorbers:

- (1) 26.7 parts of a 20% solution of benzotriazole-1 in N-methylpyrrolidone;
- (2) 26.7 parts of a 20% solution of benzophenone-2 in propylene carbonate;
- (3) 20.0 parts of a 20% solution of oxanilide-1 in propylene carbonate; and
- (4) 10.0 parts of a 20% solution of benzotriazole-2 in propylene carbonate.

The resulting film was haze-free, colorless and substantially free of exudate, confirming that each of the absorbers had a molecular weight less than that which will form a visible separate phase in the poly(vinyl fluoride), and that each absorber was added in a quantity below the saturation level of that absorber. A 1.3 mil film had an absorbance of 3.9 at 300 nm and .21 at 400 nm.

Example 5

A casting mixture was prepared by sand milling 1000 parts 33.3% poly(vinyl fluoride) dispersion in propylene carbonate, to which were added, with stirring, the following solutions of ultraviolet light absorbers:

- (1) 15.8 parts 20% solution of benzotriazole-1 in N-methylpyrrolidone;
- (2) 15.8 parts of a 20% solution of oxanilide-1 in propylene carbonate;
- (3) 15.8 parts of 20% solution of benzophenone-1 in N-methylpyrrolidone;
- (4) 11.8 parts of 20% solution of benzotriazole-2 in propylene carbonate;
- (5) 7.9 parts of 20% solution of benzotriazole-3 in N-methylpyrrolidone;
- (6) 7.9 parts of 20% solution benzophenone-2 in propylene carbonate;
- (7) 7.9 parts of 20% solution of hindered amine light stabilizer-1 in N-methylpyrrolidone; and
- (8) 7.9 parts of 20% solution of hindered amine light stabilizer-2 in N-methylpyrrolidone.

This dispersion was treated as in Example 3 to give a haze-free, clear, colorless 1.3 mil film substantially free of exudate. The absorbance of this film was 3.9 at 300 nm and .2 at 400 nm.

Comparative Examples A-I

In Comparative Examples, A-I, poly(vinyl fluoride) films were prepared and tested containing a variety of UV screeners. A single screener was used in each Comparative Example at a concentration of 3 phr. While below the total screener concentration in Examples 1-5 above, the resulting films were unsatisfactory in one or more respects, as indicated below. Accurate absorbancy values cannot be obtained on inhomogeneous systems. On the basis of Beer's Law, they are calculated to be 2.5 to 2.75 @ 300 nm compared to 3.1 to 4.5 for the films of Examples 1-5.

Table for Comparative Examples A-I

<u>Example</u>	<u>UV Screener/ Hindered amine</u>	<u>T10*</u>	<u>Description of 1.2 mil film @ 3 phr additive</u>
A	Benzotriazole-1	270	Moderate-Severe liquid surface exudate
B	Benzotriazole-2	275	Severe surface haze & exudate
C	Benzotriazole-3	>250	Severe internal haze & powdery exudate
D	Benzotriazole-4	230	Severe powder exudate
E	Benzophenone-1	275	Severe oily surface exudate
F	Benzophenone-2	245	General film haze & crystalline exudate
G	Oxanilide-1	>250	Sticky, oily surface exudate
H	Hindered Amine-1	280	Severe sticky, oily surface exudate
I	Hindered Amine-2	275	Severe powdery surface exudate

*T10 - During thermogravimetric analysis (heating at 10°C/min) T10 is the temperature in °C at which 10% of the material is lost.

Claims

1. In a fluoropolymer film comprising up to 10 weight % of ultraviolet light absorber, the improvement wherein the film comprises at least two ultraviolet light absorbers, each absorber having a molecular weight of less than 5000 and less than that which will form a visible separate phase in the fluoropolymer; each absorber present in a quantity of up to 2.5 parts by weight per hundred parts by weight of resin, but below the saturation level of that absorber in the fluoropolymer; and each absorber having a molecular structure which differs chemically from each other absorber.
2. A film of claim 1 comprising at least three ultraviolet light absorbers.
3. A film of claim 1 or 2 wherein the ultraviolet light absorbers are selected from hydroxy benzophenones, hydroxy benzotriazoles, oxanilides and substituted cyanoacrylates.
4. A film of claim 1, 2 or 3 wherein the fluoropolymer consists essentially of poly(vinylfluoride).
5. A film of any one of claims 1 to 4 wherein the volatility of each absorber is such that the temperature at which 10% of the absorber is volatilized is greater than 200°C.
6. A film of any one of claims 1 to 5 which is substantially unoriented.

7. A film of claim 3 wherein the ultraviolet light absorbers comprise from 0.5 to 3.5 parts of at least one benzotriazole, from 0.5 to 2.0 parts of at least one benzophenone, and from 0.5 to 2.0 parts of at least one oxanilide.
8. A film of any one of Claims 1 to 7 containing from 1 to 7.5 weight % of ultraviolet light absorber.
9. A film of any one of Claims 1 to 8 further comprising up to 2 parts per hundred of at least one hindered amine light stabilizer.

Patentansprüche

1. In einer Fluorpolymerfolie, die bis zu 10 Gew.-% Ultraviolettlicht-Absorber umfaßt, besteht die Verbesserung darin, daß die Folie wenigstens zwei Ultraviolettlicht-Absorber umfaßt, wobei jeder Absorber ein Molekulargewicht von weniger als 5 000 und weniger als dasjenige, das in dem Fluorpolymer eine sichtbare getrennte Phase bildet, besitzt, jeder Absorber in einer Menge von bis zu 2,5 Gewichtsteilen auf 100 Gewichtsteile Harz, jedoch unterhalb des Sättigungsniveaus des Absorbers in dem Fluorpolymer vorhanden ist und jeder Absorber eine Molekulargewichtsstruktur besitzt, die sich voneinander unterscheiden.
2. Folie nach Anspruch 1, die wenigstens drei Ultraviolettlicht-Absorber umfaßt.
3. Folie nach Anspruch 1 oder 2, worin die Ultraviolettlicht-Absorber ausgewählt sind aus Hydroxybenzophenonen, Hydroxybenzotriazolen, Oxaniliden und substituierten Cyanoacrylaten.
4. Folie nach Anspruch 1, 2 oder 3, worin das Fluorpolymer im wesentlichen aus Poly(vinylfluorid) besteht.
5. Folie nach einem der Ansprüche 1 bis 4, worin die Flüchtigkeit eines jeden Absorbers so ist, daß die Temperatur, bei der 10 % des Absorbers verflüchtigt werden, höher ist als 200 °C.
6. Folie nach einem der Ansprüche 1 bis 5, die im wesentlichen unorientiert ist.
7. Folie nach Anspruch 3, worin die Ultraviolettlicht-Absorber 0,5 bis 3,5 Teile von wenigstens ein Benzotriazol, 0,5 bis 2,0 Teile von wenigstens einem Benzophenon und 0,5 bis 2,0 Teile von wenigstens einem Oxanilid umfassen.
8. Folie nach einem der Ansprüche 1 bis 7, die 1 bis 7,5 Gew.-% Ultraviolettlicht-Absorber enthält.
9. Folie nach einem der Ansprüche 1 bis 8, die außerdem bis zu 2 Teile pro Hundert von wenigstens einem gehinderten Amin-Lichtstabilisator umfaßt.

Revendications

1. Dans un film de polymère fluoré comprenant jusqu'à 10% en poids d'agent d'absorption de lumière ultraviolette, le perfectionnement selon lequel le film comprend au moins deux agents d'absorption de lumière ultraviolette, chaque agent d'absorption ayant un poids moléculaire inférieur à 5000 et inférieur à celui qui donnerait lieu à la formation d'une phase séparée visible dans le polymère fluoré, chaque agent d'absorption étant présent en une quantité allant jusqu'à 2,5 parties en poids pour 100 parties en poids de résine, mais inférieure à la quantité saturante de cet agent d'absorption dans le polymère fluoré, et chaque agent d'absorption ayant une structure moléculaire qui diffère chimiquement de celle de chaque autre agent d'absorption.
2. Un film selon la revendication 1 comprenant au moins trois agents d'absorption de lumière ultraviolette.
3. Un film selon la revendication 1 ou 2 dans lequel les agents d'absorption de lumière ultraviolette sont choisis parmi les hydroxy benzophénones, les hydroxy benzotriazoles, les oxanilides et les cyanoacrylates substitués.
4. Un film selon la revendication 1, 2 ou 3 dans lequel le polymère fluoré est essentiellement constitué de poly(fluorure de vinyle).
5. Un film selon l'une quelconque des revendications 1 à 4 dans lequel la volatilité de chaque agent d'absorption est

EP 0 424 153 B1

telle que la température à laquelle 10 % de l'agent d'absorption sont volatilisés est supérieure à 200 °C.

6. Un film selon l'une quelconque des revendications 1 à 5 qui est sensiblement non orienté.

5 7. Un film selon la revendication 3 dans lequel les agents d'absorption de lumière ultraviolette comprennent de 0,5 à 3,5 parties d'au moins un benzotriazole, de 0,5 à 2,0 parties d'au moins une benzophénone et de 0,5 à 2,0 parties d'au moins un oxanilide.

10 8. Un film selon l'une quelconque des revendications 1 à 7 renfermant 1 à 7,5 % en poids d'agent d'absorption de lumière ultraviolette.

9. Un film selon l'une quelconque des revendications 1 à 8 renfermant en outre jusqu'à 2 parties pour cent d'au moins un agent photostabilisant à amine encombrée.

15

20

25

30

35

40

45

50

55